

EXCEL MARSTRON +

Excel Marstron has been upgraded in 2012 to Excel Marstron +. The rope now has a blended polypropylene and Dyneema cover to extend the abrasion resistance of the line through cleats and ratchet blocks.



APPLICATIONS

MATERIAL CORE:

COVER:

CONSTRUCTION TWISTED FIBRE CONSTRUCTION: 8 STRAND BRAIDED CORE CONSTRUCTION:

16 PLAIT BRAIDED COVER CONSTRUCTION:

PROPERTIES RELATIVE DENSITY: CHEMICAL RESISTANCE:

MELTING POINT: CRITICAL TEMPERATURE: Sheets, Floating Ropes

Manufactured from Polypropylene Very light weight Low water absorption Manufactured from Dyneema Polypropylene blend Good abrasion Very light weight Very low water absorption

Improved abrasion resistance


Firmer rounder rope, aids handling Flexible product and easily handled Torque balanced

Protects core from dirt and abrasion Round and firm construction Smooth profile while maintaining grip

0.93 (Floats) Exact figure varies with diameter Excellent resistance to most chemicals (additional information available on request) 140°C 80°C (exposure to temperatures over this will result in permanent strength loss)

ELONGATION

Typical working elongation (for a bedded in a rope): @ 10% of break load: 3.7% @ 20% of break load: 5.3%



PERFORMANCE

DIAMETER	CIRCUMFERENCE	MASS		AVERAGE STRENGTH			MIN STRENGTH		
mm	Inch	g/m	lb/100 ft	kg	lb	kN	kg	lb	kN
6	7/32	18.1	1.21	650	1430	6.4	585	1287	5.7
7	1/4	21.2	1.42	1026	2257	10.1	975	2145	9.6
8	5/16	28.5	1.91	1092	2402	10.7	983	2163	9.6

Marlow Ropes Ltd Ropemaker Park Hailsham East Sussex, BN27 3GU England

Marlow Ropes, Inc. Cordage Business Park Plymouth MA 02360 USA

www.marlowropes.com UK: +44 (0) 1323 444 444 sales@marlowropes.com US: +1 508 830 444 salesusa@marlowropes.com



Certification Number 315 ISO 9001

Disclaimer

Marlow Ropes Ltd endeavours to ensure that all products are manufactured to the highest standard, these guidelines are not intended and do not create any warranties, express or implied.

Marlow Ropes Ltd expressly disclaims warranties or representations of any kind, express or implied, including the implied warranties of merchantability and fitness for a particular purpose.

Marlow Ropes Ltd shall not be liable for any consequential, incidental or contingent damages whatsoever stemming from the use of these guidelines. MA-DA-032A | ISSUE NO.3